



INTEGRAL CIPO LLC

TEST LINER

Property	Values					
Substance, g/m ²	100 ±3	110 ±3	120 ±3	125 ±3	135 ±3	150 ±3
BST, kPa, min	185	225	280	320	350	375
SCT CD, kN/m, min	1,92	2,12	2,31	2,40	2,60	2,88
Cobb60, g/m ² , min	40	40	40	40	40	40
Moisture, %	6 - 9	6 - 9	6 - 9	6 - 9	6 - 9	6 - 9

