



INTEGRAL CIPO LLC

KRAFT LINER

Ortalama Değerler, Typical Values

Parametre Parameter	Birim Unit	test metodu standard	70	100	110	135
Gramaj Grammage	gr/m ²	ISO 536	70	100	110	135
Nem Moisture	%	ISO 287	7	7	7	7
SCT	kN/m	ISO 9895	1,15	1,7	1,8	2,2
Patlama	kPa	ISO 2759	165	210	225	265
RCT	kN/m	ISO 12192	0,45	0,85	1,1	1,4
CoBB,60	g/mn	ISO 535	50	50	50	50

Garanti Edilen Değerler, Guaranteed Values

Parametre	Birim Unit	Test Metodu Standard	70	100	110	135
Gramaj Grammage	g/m ²	ISO 536	+-%3	+-%3	+-%3	+-%3
Nem	%	ISO 287	+,-1,5	+,-1,5	+,-1,5	+,-1,5
SCT,min	kN/m	ISO 9895	0,9	1,5	1,6	1,7
Patlama	kPa	ISO 2759	135	180	190	200
Bobin çapı Bobbin Diameter	cm		140	140	140	140
Mihver Çapı Core Diameter	mm		100	100	100	100

Öçlüm koşullari: Bağıl nem- %50 \pm 2, Sicaklik 23 \pm 1°C

Measuring conditions: Relative Humidity - %50 \pm 2, Temperature 23 \pm 1°C

Ocak 2017 itibariyle geçerlidir. Valid starting from January 2017